

LUTRADUR®

Style	Weight		Thickness (mils)	Air Perm (cfm/ft ²)	Mullen Burst (psi)
	(g/m ²)	(oz/yd ²)			
LD-7225	25	0.74	4	1150	30
LD-7240	40	1.18	7	900	50
LD-7250	50	1.48	11	840	60
LD-7270	70	2.06	13	670	82
LD-7210	100	2.95	20	420	120

MFC-348-08

These are typical values and not intended as specifications

Lutradur® is a registered trademark of Freudenberg Spunweb Company.

Lutradur® is a unique performance oriented spunbond polyester media with these distinguishing characteristics.

- Spunbond continuous filament fiber sheet
- High strength to weight ratio
- No chemical binder - 100% Polyester
- Excellent pleatability and thermal moldability
- Low shrinkage
- Excellent dimensional stability
- Does not ravel or fray
- Coarse fiber for high flow rates

