

# TYPAR®

Style	Denier*	Weight (oz/yd2)	Thickness (mils)	Frazier Air Perm (cfm/ft2)	Textest Air Perm (cfm/ft2)	Mullen Burst (psi)	Grab Tensile (MD/CD, lbf)	Trap Tear (MD/CD, lbf)
3091L	L	0.90	8	540	635	21	20/15	6/5
3121L	L	1.30	9	380	380	28	32/28	12/9
3161L	L	1.60	10	250	255	35	40/22	12/10
3409L	L	4.00	15	29	25	110	120/80	35/20
3609L	L	6.00	20	16	13	177	170/110	60/35
3121N	S	1.30	10	650	635	40	55/50	28/24
3141N	S	1.40	10	590	575	44	60/50	30/25
3151C	S	1.60	12	530	560	52	70/60	33/29
3201A	S	1.90	12	400	414	57	80/74	37/34
3301Y	S	3.00	14	180	160	100	133/135	50/50
3801N	S	8.00	25	12	N/A	N/A	350/356	97/87

\* L=Low Denier, S=Standard Denier

*These are typical values and not intended as specifications*

*A white spunbonded filter media containing 100% polypropylene fibers.*

