

# UNIPOLY

Style	Bond	Weight		Thickness (mils)	Air Perm (cfm/ft <sup>2</sup> )	Mullen Burst (psi)	Grab Tensile (MD/CD, lbf)
		(g/m <sup>2</sup> )	(oz/yc <sup>2</sup> )				
UNIPOLY 50 MRP	Point	17	0.50	3	917	13	9/6
UNIPOLY 60 MRF	Flat	19	0.60	5	983	17	7/6
UNIPOLY 75 MRF	Flat	25	0.75	5	950	18	9/7
UNIPOLY 100 MRF	Flat	34	1.00	6	615	19	14/12
UNIPOLY 135 MRF	Flat	46	1.35	8	498	27	21/18
UNIPOLY 200 MRF	Flat	68	2.00	9	298	39	35/30
UNIPOLY 300 MRF	Flat	102	3.00	12	241	40	39/40

MFC-348-08

*These are typical values and not intended as specification:*

*Unipoly, Spunbond Polyester is a unique performance oriented spunbond polyester media with the distinguishing characteristics*

- Spunbond continuous filament fiber sheet
- High strength to weight ratio
- No chemical binder - 100% Polyester
- Excellent pleatability and thermal moldability
- Low shrinkage
- Excellent dimensional stability
- Does not ravel or fray
- Finer fabric for good uniformity and flow rate



9775 International Blvd., Cincinnati, Ohio 45246, (513) 874-6510, [www.midwestfiltration.com](http://www.midwestfiltration.com)